

COMPLETE DRILLINGS.

NAME *T. S. S. "TAHITI"*

Report *SYDNEY N.S.W.* No. $\left. \begin{matrix} 10678 \\ 10774 \\ 10998 \end{matrix} \right\}$

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in 20^{th} of an inch.

PLATE.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.	
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.			
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		
DECK STRAKE	20	20	20	✓	✓	12	12	12	✓	✓	12	14	14	✓	✓		
W	N.	18	18	18	✓	✓	12	12	12	✓	✓	12	12 $\frac{1}{2}$	12 $\frac{1}{2}$	✓	✓	
DECK STRAKE M		15	14 $\frac{1}{2}$	14 $\frac{1}{2}$	$\frac{1}{2}$	$\frac{1}{2}$	12	12	12	✓	✓	12	12	12	✓	✓	
Below	A.	13	11 $\frac{1}{2}$	12	1 $\frac{1}{2}$	1	10	10	10	✓	✓	10	11 $\frac{1}{2}$	11 $\frac{1}{2}$	✓	✓	
"	K.	14	12 $\frac{1}{2}$	12	1 $\frac{1}{2}$	2	11	10 $\frac{1}{2}$	10 $\frac{1}{2}$	$\frac{1}{2}$	$\frac{1}{2}$	11	11 $\frac{1}{2}$	12	✓	✓	
"	M.	13	11 $\frac{1}{2}$	12	1 $\frac{1}{2}$	1	10	9 $\frac{1}{2}$	9 $\frac{1}{2}$	$\frac{1}{2}$	$\frac{1}{2}$	10	12 $\frac{1}{2}$	11	✓	✓	
"	H.	14	12 $\frac{1}{2}$	12 $\frac{1}{2}$	1 $\frac{1}{2}$	1 $\frac{1}{2}$	11	11	10	✓	1	11	10 $\frac{1}{2}$	10 $\frac{1}{2}$	$\frac{1}{2}$	$\frac{1}{2}$	
"	G.	14	12	12 $\frac{1}{2}$	2	1 $\frac{1}{2}$	11	11	11	✓	✓	11	12	12	✓	✓	
"	F.	15	14	14	1	1	12	12	12	✓	✓	12	12	12	✓	✓	STAGLER STAGLER
"	CEMENT					11	11	11	✓	✓	11	10	11	1	✓	STAGLER STAGLER	
"																	
"						CEMENT					11	14	10	✓	✓	Joe C. Crankin	

Drillings at ends to be made in the vicinity of the peak bulkheads.

Lloyd's Register
Foundation