

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL. FORGINGS.

Made by Messrs. Wm. Beardmore & Co., Ltd., GLASGOW.

For Messrs. D. Rowan & Co., Ltd., Eng. No. 966 for Messrs. Blythswood S.B. Co. Ltd.

Ship No. 35.

Date.	Test Batch No.	No. of Pieces.	Description.	Charge Mark.	Sample No.	Dia. Thickness.	Area.	Tons per square inch.	Extension on 3 inches.
									% Bend
F.	3061	1	Conn. Rod			.798	.50	31.0	31 180°
"	3062	1	do.			"	"	31.0	28 "
"	3063	1	do.			"	"	31.4	30 "
"	3064	1	Propeller Shaft			"	"	30.2	28 "
"	3053	1	Coupling End			"	"	30.2	28 "
"	3054/5	2	do.			"	"	30.0	27 "
"	3056/8	3	Crank Pins			"	"		
"	3059/60	1	Journal & 1 end			"	"	31.0	30 "
"	3065	1	Propeller Shaft			"	"	30.0	29 "
"	3066	1	Thrust Shaft			"	"	30.0	28 "
"	3067	1	Inter. Shaft			"	"	29.8	30 "
"	3068	1	do.			"	"	30.2	31 "
"	3069	1	do.			"	"	30.0	27 "
"	3070	1	do.			"	"	30.4	30 "
"	3071	1	do.			"	"	28.8	33 "
"	3072	1	do.			"	"	28.4	30 "

Chas. S. Porter

Glasgow. 20/12/1914



© 2021

Lloyd's Register
Foundation

U 66-00 86