

Coatings ..... Ceiling ..... Scuppers ..... Masts, Yards  
Beams & Fastenings ..... Cement or Asphalt ..... Cargo Hatchways ..... Condition, h  
Outside Plating ..... (State which.) ..... (State i  
Sails.....  
Equipment  
Anchors, No  
Cables (Sta  
" length  
" Rule  
Hawser &  
Standing a

VESSEL'S NAME "BALTAVIA" Report No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in  $20^{\text{ths}}$  of an inch.

STRAKE.	AMIDSHIP.						FORWARD.				AFT.				REMARKS.	
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.		Std.
AWNING																
SPAR SHEER STRAKE .....	12	12	11½	-	½	7	7½	8	-	-	7	8	7½	-	-	
Strake below.....	10	11½	10	-	-	7	7	7	-	-	7	8	7½	-	-	
MAIN SHEER STRAKE .....	13	13	13	-	-	10	11	11	-	-	10	10	12	-	-	
1st Strake below .....	12	10½	10½	1½	1½	9	8	9	1	-	9	9	9	-	-	
2nd " .....	12	11	11½	1	½	9	9	9	-	-	9	10	8½	-	½	
3rd " .....	12	10½	11	1½	1	9	8½	9	½	-	9	8½	8½	½	½	
4th " .....	12	10½	12	1½	-	9	9½	9½	-	-	9	8	7	1	2	
5th " .....	12	10½	10½	1½	1½	9	9	9½	-	-	9	9	9	-	-	
6th " .....	12	11½	11	½	1.	9	8	8	1	1	9	8	8	1	1	
7th " .....						9	9	5*	-	-	9	10½	9	-	-	
8th " .....						9	8	7½	1	1½	9	8½	8½	½	½	
9th " .....						9	8	7½	1	1½	9	8½	11	½	-	

Drillings at ends to be made in the vicinity of the peak bulkheads.

Character Assigned

Deferred for

Lloyd's Register Foundation

SEP 19