

TELEGRAMS. "LLOYD'S TEST." GLASGOW
 TELEPHONE, KINNING PARK 215.

LLOYD'S PROVING HOUSE,
 82 ST. JAMES' STREET,
 KINNING PARK.

2

Messrs Scottish Concrete Pipe Co. Ltd.
 Greenock



Glasgow, 31st May 1919

The following are particulars of Compression Tests applied to
 Three Concrete Blocks

Number of Test	DESCRIPTION	WEIGHT lbs. ozs.	DEPTH Inches	SECTIONAL		ULTIMATE CRUSHING STRESS			MARKS
				Dimensions Inches	Area Inches	Total Tons	Per Sqr. Inch Tons	Per Sqr. Inch Pounds	
4192	1 Concrete Block	5. 10	4	4x4.1	16.4	14.13	1.04	2329	M3.
4193	1 do	5. 10 $\frac{1}{4}$	4	4x4.15	16.6	15.0	.90	2016	23/5/19 JMR
4194	1 do	5. 9 $\frac{1}{2}$	4	4x4.15	16.6	15.59	.93	2083	do
								36428 2143.	do

By request of Messrs Scottish Concrete Pipe Co. Ltd. I attach hereto
 particulars supplied by them, with reference to above cubes

J. H. Butler
 Supt. Pro Tem



© 2021

Lloyd's Register
 Foundation

W737-0024

