

Concrete Coasting Boat. Esq. Taverham

TESTING & EXPERIMENTAL WORK

BY THE

LONDON

14<sup>th</sup> April 1919

four-inch cubes of concrete received from yourselves.

Age 28 days.

Made 17<sup>th</sup> March 1919

Proportions:-  
Ballast & Sand  
Ham River  
Portland Cement,  
Peters Brand,  
2.1.1

DESCRIPTION	WEIGHT	DIMENSIONS	BASE AREA	TOTAL	CRUSHING STRENGTH
Made 17 <sup>th</sup> March 1919	5.25	3.95 3.95 4.00	16.05	62.000	3860
Proportions:- Ballast & Sand Ham River Portland Cement, Peters Brand, 2.1.1	5.30	3.95 3.95 4.00	16.08	73.900	4570
	5.30	3.95 3.95 4.00	16.08	71.800	4470

J. Bradford & Co.

Leepersale Road, Hemerton L.G.

David Kirkaldy & Co.



© 2021

Lloyd's Register Foundation