

Shell  $\frac{11}{32}$ " thick - Rivets  $\frac{1}{2}$ " dia in  $1\frac{5}{8}$ " drilled holes.  
Double butt straps 1" wide x  $\frac{1}{8}$ " thick Inside butt straps not less than  $\frac{1}{32}$ " thick  
Combustion Chamber stays marked @  
Strength of Joint Plate 85%  
Rivets 85.6%

WORKING PRESSURE 180 L<sup>bs</sup> PR SQ INCH

TESTED TO 360 LBS LORD'S REQUIREMENTS

TESTED TO 360 LBS LORD'S REQUIREMENTS

5<sup>th</sup> Dec 1904

LLOYD'S REGISTER  
5/12/64  
ABERDEEN OFFICE  
J.E.H.  
OF BUILDING



J<sup>d</sup> Abernethy & C<sup>d</sup>

Main Boiler R<sup>d</sup> 696


J. Butcher S. S. R<sup>d</sup> 245

S. S. "Ballochbuie"

Abn Rpt. R<sup>d</sup> 5396

Test Mark

R<sup>d</sup> 415  
Lloyds Test  
360 lbs  
30.5.05. J.C.L.



RETAIN



© 2021

Lloyd's Register  
Foundation

W962-0018