

Th. *1/2 Anthony Hope*  
Hull Rpt No: 26666

# Lloyd's Register of British & Foreign Shipping.

LLOYD'S REGISTER  
OF SHIPPING.  
26 MAY 1913  
HULL

Order 11335. Surveyors' Office, DÜSSELDORF.

This is to certify, that *Karl Hauss* the undersigned surveyor to this society tested in the works of *Messrs. Phoenix & Al. Hördter Verein* of *Hörde* the *annealed Siemens-Martin boilersteel plates* specified hereunder, ordered by *Messrs. Chas. S. Holmes & Co. Limited* of *Hull* for the ship No. Boiler No. *1014* and that the results of tests were as are set forth below.

Number of pieces.	Dimensions.			Intended for	Sample number	Charge number	Tensile tenacity			Elongation in 200 mm. in %.	Bending tests	
	Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered.
1	12'9"	10'	15/32	Shellplate	182	212	28-32	29	30.7	24	good	good
1	29'6 1/2"	"	"	"	52	"	"	"	30.4	21.5	"	"
1	7'5" R	5'7 1/2"	17/16	Endplate	13	68	32	26-30	26	27.6	26	"
1	7'4" R	"	17/4	"	14	"	"	"	27.9	25	"	"
1	7'4" R	10'13/4	17/32	"	17	"	"	"	26.9	28	"	"
1	"	"	15/16	"	9	"	"	"	28.4	25	"	"
1	"	"	"	"	9	"	"	"	27.4	27	"	"
1	"	"	"	"	C	"	"	"	27.6	27	"	"
1	7'5 1/2"	9'11 1/2"	5 1/4"	tribeplate	1	"	"	"	28.5	28	"	"
2	"	"	"	"	4	"	"	"	27.4	26	"	"
1	9'4 1/2"	4'5"	7/8"	back tribepl	2	"	"	"	26.9	26	"	"
2	7'6"	4'11 1/2"	7/8"	do.	3	"	"	"	27.4	29	"	"
1	9'3 1/4"	4'5"	23/32"	ch. back	12	"	"	"	26.4	26	"	"
2	7'4 1/2"	4'11 1/2"	"	"	12	"	"	"	26.4	26	"	"
1	4'2"	2'11 1/2"	11/16"	" top	11	"	"	"	28.5	27	"	"
2	5'9"	"	"	"	10	"	"	"	27.7	24	"	"
1	18'4"	"	23/32"	" side	6	"	"	"	27.8	26	"	"
1	13'10 1/8"	"	11/16"	"	10	"	"	"	27.7	24	"	"
1	"	"	"	"	11	"	"	"	28.5	27	"	"
2	10'	1'6 1/2"	7/8"	bricksprays	8	212	28-32	29	30.6	24	"	"
2	9'7"	"	17/16"	"	7	"	"	"	30	24	"	"
1	2'6"	2'2"	15/32"	shell liner	182	"	"	"	30.7	24	"	"
					C	"	"	"	30.4	21.5	"	"

This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:—

"While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood that neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error of judgment, default, or negligence of the Surveyors, or other Officers or Agents of the Society."

N.B.—Material with less than 26 Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially sanctioned by the Committee.

1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0,635 Tons per square inch.



Order 11335. P 1014.

Messrs. Chas. F. Holmes & Co. Ltd. Bill

Batch number.	Dimensions.			Designed for	Sample number	Charge number	Tensile tenacity			Elongation in 200 mm. in %	Bending tests		Remarks.
	Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered.	
Number of plates													
3	3'2 1/2"	1'3"	7/8"	girders	2	6832	26.30	26.30	26.9	26	good	good	
3	"	"	"	"	15	"	"	"	27.4	25	"	"	
6	"	1'4 1/4"	"	"	"	"	"	"	"	"	"	"	
10	"	"	"	"	16	"	"	"	27.4	27.5	"	"	

Tested and inspected on the 16th, 18th, 21st, 25th April, 5th May 1913.

Charles Stamps



© 2021

Lloyd's Register Foundation

W967-0083 2/2



1014



© 2021

Lloyd's Register  
Foundation