

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 19

# Lloyd's Register of Shipping.

Order: 11049.

(Report on Machinery, No. 48379 Port **GLASGOW**)

No. **25816** ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by **Messrs. Dortmunder Union** of **Dortmund** for the Engines No. **870** being constructed by **Messrs. David Rowan & Co.** of **Glasgow** for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to **Glasgow.**

on Forgings or Castings.

**Düsseldorf 9th November 1927.**

Lloyd's

No. **2174.**

**J.O.S. 11.27.**

*Yul. Quast*  
Surveyor to Lloyd's Register

	<del>STEAM SHAFT</del> 1 interm. shaft <del>REVERSE SHAFT</del>	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.  SCREW SHAFT.
Material* ...	<b>Annealed Sien. Mart. Ingot Steel</b>			
made ...	<b>forged</b>			
annealed ...	<b>Yes</b>			
ensions, Forgings	<b>343 mm Ø</b>			
ght, Castings ...				
gress on } nspection }	<b>rough turned</b>			
sts on Standard Test Pieces.	<b>.798 3"</b>			
ile Test— ons per square inch	<b>31.1</b>			
xtension per cent	<b>26.3</b>			
Bending Test— ngle before fracture	<b>120 degr. good</b>			
es when Inspected	<b>8.11.27.</b>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

e (if any chargeable) £

To be paid at **Düsseldorf.**

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

W98-0054

843-44