

DUBLIN, *14 July* 1947.

ANSD

MURCHU.

Report DUB

No. 6017

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses. in *March*

The thicknesses are in DECS, of an inch.

1945

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thick-ness.	Thickness by drilling.		Diminution if any.		Original Thick-ness.	Thickness by drilling.		Diminution if any.		Original Thick-ness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
1 SHEER STRAKE..																			
2 below.....																			
3 STRAKE	G	40	40	37			27	32	40			27	35	30					
4 STRAKE below	F	30	30	30			27	27	27			27	25	25					
5 "	E	32	27	42			27	25	25			27	27	20					
6 "	D	35	32	31			27	30	30			27	27	27					
7 "	C						30	30	25			32	30	30					
8 "	B						32	25	30										
9																			
10																			
11																			
12																			
13																			
14																			
15																			
16																			
17																			
18																			
19																			
20																			

This copy to be retained in office

© 2020

Bm

Drillings at ends to be made in the vicinity of the peak bulkheads

This copy to be retained in office

© 2020

OBM

Lloyd's Register
Foundation

Yours faithfully